



Silicone Technologies, LLC

359 Hill Street, Biddeford, ME 04005 •
Tel: (207) 283-6422 • Fax: (207) 283-6551
www.crisil-silicones.com

ISO 9001:2000 Certified

CRI-SIL Silicone Technologies, LLC
359 Hill Street
Biddeford, Maine 04005
(207) 283-6422

PRODUCT

CSB260

Product Description

CRI-SIL HCR Silicone Rubber CSB260 is an un-catalyzed 60 durometer non-post cure silicone base. Which when cured properly will exhibit low compression set and good heat age resistance.

Cure Conditions:

Catalyzed with 0.4 pph of DBPH* to 100 pph base
Press Cured: 10 min @ 350°F

Properties

Typical Results

Plasticity	-	286
Specific Gravity		1.17
Durometer (Shore A)		62
Tensile psi		1230
Elongation %		346
100% Modulus		299
Compression Set 22hrs @ 350°F, %		14
Heat Age 70Hrs @ 437°F		
Hardness Change, pts		+7
Tensile Change, %		-31
Elongation Change, %		-41

*2,5-dimethyl-2,5-di(t-butylperoxy)hexane 100% active



<p>Key Features</p> <ul style="list-style-type: none">-Low Compression Set-No Post Cure-Blendable-Versatility for any number of applications <p>Storage and Shelf Life</p> <p>When stored at or below 32C (90F), the CSB260 has a shelf life of 12 months from the date of manufacture.</p> <p>Packaging</p> <p>CRI-SIL CSB260 is supplied in 50 lb and 1000 lb boxes, net weight.</p>	<p>Fabrications</p> <p>Fabricators should make their selection of peroxide catalyst based of their specific fabrication method(s), desired properties, and safety considerations.</p> <p>The optimum cure cycle will greatly depend on the method of processing used and the physical dimensions of the vulcanized product. Specific application may require the use of an air oven post cure.</p> <p>In addition our CRI-SIL dispersions (CSD) can be added to these bases to improve various attributes.</p> <table border="1"><thead><tr><th><u>Dispersion</u></th><th><u>Use when you want to</u></th></tr></thead><tbody><tr><td>CSD002-HA</td><td>To Improve heat age resistance</td></tr><tr><td>CSD005-MO</td><td>To remove bloom issues from 2,4- Dichlorobenzoyl peroxide and to improve hydrocarbon oil resistance</td></tr><tr><td>CSD006-PA</td><td>To reduce plasticity</td></tr><tr><td>CSD0015-5M</td><td>To lower material costs and increase specific gravity</td></tr><tr><td>CSD0016-FR</td><td>To improve the flame resistance</td></tr></tbody></table> <p>Please see specific CSD Technical Data Sheets of additional information.</p>	<u>Dispersion</u>	<u>Use when you want to</u>	CSD002-HA	To Improve heat age resistance	CSD005-MO	To remove bloom issues from 2,4- Dichlorobenzoyl peroxide and to improve hydrocarbon oil resistance	CSD006-PA	To reduce plasticity	CSD0015-5M	To lower material costs and increase specific gravity	CSD0016-FR	To improve the flame resistance
<u>Dispersion</u>	<u>Use when you want to</u>												
CSD002-HA	To Improve heat age resistance												
CSD005-MO	To remove bloom issues from 2,4- Dichlorobenzoyl peroxide and to improve hydrocarbon oil resistance												
CSD006-PA	To reduce plasticity												
CSD0015-5M	To lower material costs and increase specific gravity												
CSD0016-FR	To improve the flame resistance												

These values are not to be used to set specifications. Each user must evaluate this product for his or her intended use. All information is given in good faith, without warranty, representation, inducement or a license of any kind. CRI-SIL does not assume any legal responsibility for use of or reliance upon same. No warranty or representation is given that CRI-SIL products described will be suitable in buyers and or users formulations or processes for any particular end use. No representation is given as to freedom from patent infringement. Materials not manufactured or supplied by CRI-SIL may present hazards in handling and use. Contact supplier or the manufacturer for all information specific to this these matters