

CST3144U

Description: CST3144B is a non-curing, thixotropic silicone strand sealant deigned to be used in water-tight and gas-block cable constructions.

Key Features

- Good process-ability for sealing of wire strands
- Designed to meet or exceed MIL-C-915, MIL-C-23206 and MIL-C-24145

Applications

- Wire Strand Sealant

<u>Property</u>	<u>Typical Value</u>
Color and Visual Appearance	White, Smooth
Consistency	Paste, Self-Leveling to Prevent Wire Channeling
Gravity	1.59
Pounds/Gallon	12.7
Viscosity Brookfield, cPs	239,000
Temperature Range	-65°F to +400°F
Catalyst	None
Solids	100%
Acid Generation	None
Halogen Content	None

Materials were tested according to CRI-SIL Silicone Technologies Test Methods (CSTM).

Application Notes

Commonly CST3114U is applied at the wire standing operation by coating the center strand of a seven strand construction. Application can be made by the gravity method; however, the best results are obtained with positive pumping.

Storage and Shelf Life

When stored at or below 32C (90F), this material has a shelf life of 6 months from the date of manufacture.

Cleaning Notes

To remove paste sealant, solvents such as alcohol, toluene, xylene, petroleum spirits, or perchlorethylene may be used

Packaging

Supplied in 5-gallon pails (50 lbs.) and 55-gallong drums (500lbs)

Limited Warranty Information – Please Read Carefully

The information contained herein is offered in good faith and is believed to be accurate. However, because end-use manufacturing conditions vary, this information should not be used in substitution of actual product testing to ensure full satisfactory for the intended end use.

All information is given in good faith, without warranty, representation, inducement or a license of any kind. CRI-SIL does not assume any legal responsibility for use of or reliance upon same. No warranty or representation is given that CRI-SIL products described will be suitable in buyers and/or users formulations or processes for any particular end use. No representation is given as to freedom from patent infringement and suggestions of use shall not be taken as inducements to infringe any patent. Materials not manufactured or supplied by CRI-SIL may present hazards in handling and use. Contact supplier or the manufacturer for all information specific to this these matters

Contact Us

Visit www.cri-sil.com to learn more about the many products available to you from CRI-SIL Silicone Technologies, LLC.

Specification Writers: These values are considered "Typical Values" and therefore not intended for use in preparing specifications. Please contact CRI-SIL Silicone Technologies prior to writing specifications on these products.